

Plastic Bonded Ferrite Magnets

一般物理性能 Typical Physical Properties					
牌號 Grade	性能 Properties				
	居理溫度 Curie Temp.	最高工作溫度 Max. Oper. Temp.	剩磁溫度系數 Br Temp. Coefficient	回復磁導率 Rev. Recoil Permeability	密度 Density
	°C	°C	%/°C	μ_{rec}	g/cm^3
PBF-7	450	≤ 120	-0.2	1.3	3.6-3.8
PBF-13	450	≤ 120	-0.2	1.3	3.6-3.8
PBF-15	450	≤ 120	-0.2	1.3	3.6-3.8
PBF-17	450	≤ 120	-0.2	1.3	3.6-3.8