

Flexible Rubber Magnets

一般磁材性能 Typical Magnetic Properties					
牌號 Grade	性能 Properties				
	剩磁 Remanence (Br)	矯頑力 Coercivity (bHc)	內稟矯頑力 Intrinsic Coercivity (iHc)	最大磁能積 Max. Energy Product (BHmax)	種類 Type
	Gs	Oe	Oe	MGOe	
F-Flex 7	1800+/-50	1500+/-200	2000+/-200	0.7-0.8	Calender
F-Flex 10	1950+/-50	1550+/-100	2000+/-100	0.9+/-0.05	Calender
F-Flex 12BH	2450+/-50	1950+/-100	2600+/-100	1.45+/-0.05	Calender
F-Flex 10E	1800+/-50	1400+/-100	2000+/-100	0.75+/-0.05	Extrusion
F-Flex 12BH-E	2200+/-50	1822+/-100	2600+/-100	1.0-1.2	Extrusion